

ECOMEDICAL

TECHNICAL PROPERTIES

HARDWEARING

Resistente all'usura | Strapazierfähig
Résistant | Slitesterkt
Kulutusta Kestävä | Resistente

ELEGANTLY COMFORTABLE

Confort con Stile | Schön und Komfortabel
Beau et Comfortable | Vakkert & Behagelig
Tyylikäs & Mukava | Agradable y Comfortable

BREATHABLE

Traspirante | Atmungsaktiv
Respirant | Pustende
Hengittävä | Transpirable

EASY CARE

Facile Manutenzione | Pflegeleicht
Facile d'entretien | Lettstelt
Helppohoitoinen | Fácil Mantenimiento

ECOLOGICALLY FRIENDLY

Ecologica | Umweltfreundlich
Écologique | Miljøvennlig
Ympäristöystävällinen | Ecológico

COMPOSITION

43% Polyester
48% Modacrylic
9% Polyurethan

Materiale | Zusammensetzung
Composition | Komposisjon
Koostumus | Material

WIDTH

142 ± 2 cm

Larghezza | Breite
Laize | Bredd
Leveys | Largo

WEIGHT

425 g / m² ± 30%

Peso | Gewicht
Poids | Vekt
Paino | Peso

ABRASION

40.000 martindale
ISO 12947-1-2-3-4

Abrasione | Abriebfestigkeit
Abrasion | Slitestyrke
Hankauskesto | Abrasión

LIGHTFASTNESS

5 blue scale (SCALE 1-8)
ISO 105 B02

Solidità alla Luce | Lichtechtheit
Tenue à la Lumière | Lysekthet
Valonkesto | Solidez a la Luz

4 / 4 (Wet/Dry)

3(Wet) only dark colors
ISO105X12-DIN54021

RESISTANCE TO RUBBING

Resistenza agli sfregamenti | Reibechtheit
Solidité des Tintes | Gniekthet
Värinkesto | Resistencia al Frotamiento

PILLING

5 (scale 1-5)
ISO 12945-2

Pilling | Pilling
Pilling | Pilling
Nyppyntyminen | Pilling

CLEANING

   

Pulizia | Reinigung
Nettoyage | Rengjøring
Puhdistus | Limpieza

FLAMMABILITY

BS 5852 section 4

Infammabilità | Schwerentfambarkeit
Non feu | Flammesikring
Paloluokitus | Infamabilidad

It also passes:

DIN EN ISO 20811
ASTM 1670
SOP 12-012

